

15-30 MIL SKIDPROOF PE

	ASTM TEST METHOD	E15DBS	E30BS
THICKNESS, NOMINAL		15 MIL	30 MIL
WEIGHT		10 OZ/SQ-YD	21.6 OZ/SQ-YD
TENSILE STRENGTH	D6693	70 LBF	114 LBF
TENSILE ELONGATION	D6693	1000%	800%
TEAR RESISTENCE	D1004	8 LBF	17 LBF
MULTI-AXIAL TENSION	D5617		130%
IMPACT RESISTANCE	D1709	3600 G	2400 G
CARBON BLACK %	D1603 / D4218		2.50%
MAX TEMP USE		180 DEG F	180 DEG F
MIN TEMP USE		-70 DEG F	-70 DEG F



CONTACT US
SALES: Sam Liberto, 724.650.3592, sam@bepsinc.com
OPERATIONS: Jack Bell, 814.598.2553, jackb@bepsinc.com