

20-45 MIL REINFORCED PP

	ASTM TEST METHOD	20	36	45
THICKNESS		20 MIL	36 MIL	45 MIL
BREAKING STRENGTH	D751A	WARP 200 LBF / WEFT 200 LBF	WARP 275 LBF / WEFT 250 LBF	WARP 300 LBF / WEFT 250 LBF
TEAR STRENGTH	D751B	WARP 70 LBF / WEFT 70 LBF	WARP 70 LBF / WEFT 70 LBF	WARP 70 LBF / WEFT 70 LBF
HYDROSTATIC RESISTANCE	D751A	300 PSI	350 PSI	350 PSI
PUNCTURE RESISTANCE	FTMS 101C 2031	250 LBS	300 LBS	300 LBS
PLY ADHESION	D751	40 LBS	40 LBS	40 LBS
DIMENSIONAL STABILITY	D1204	1% MAX	1% MAX	1% MAX
LOW TEMPERATURE FLEX	D2136	-40 DEG F	-40 DEG F	-40 DEG F
STRESS CRACK RESISTANCE	D1693	3000 HOURS	3000 HOURS	3000 HOURS
UV RESISTANCE	G155	20,000 HOURS	20,000 HOURS	20,000 HOURS



CONTACT US

SALES: Sam Liberto, 724.650.3592, sam@bepsinc.com

OPERATIONS: Jack Bell, 814.598.2553, jackb@bepsinc.com