

**25-30 MIL TEXTURED PE**

	ASTM TEST METHOD	J25DT1	J30DT1
APPEARANCE		GRAY/BLACK	GRAY/BLACK
THICKNESS, NOMINAL		25 MIL	30 MIL
ASPERITY HEIGHT	D7466	>20 MIL	>20 MIL
WEIGHT (LBS/MSF/OZ-SQ.YD.)		115 LBS (16.6)	128 LBS (18.4)
CONSTRUCTION			
PLY ADHESION (LBF/IN)	D6636	15 LBS OR FTB	18 LBS OR FTB
TENSILE STRENGTH (LBF/IN)	D7003	50 MD / 62 TD	56 MD / 68 TD
TENSILE ELONGATION AT BREAK (FILM)	D7003	549 MD / 590 TD	550 MD / 585 TD
TENSILE ELONGATION AT BREAK (SCRIM)	D7003	14 MD / 24 TD	15 MD / 24 TD
TONGUE TEAR	D5884	42 MD / 50 TD	46 MD / 54 TD
GRAB TENSILE (SCRIM BREAK)	D7004	130 DD	145 DD
GRAB TENSILE ELONGATION AT BREAK (SCRIM)	D7004	39%	40%
PUNCTURE RESISTANCE	D4833	50 LBF	55 LBF
MAX TEMP USE		180 DEG F	180 DEG F
MIN TEMP USE		-70 DEG F	-70 DEG F



**CONTACT US**

**SALES:** Sam Liberto, 724.650.3592, [sam@bepsinc.com](mailto:sam@bepsinc.com)

**OPERATIONS:** Jack Bell, 814.598.2553, [jackb@bepsinc.com](mailto:jackb@bepsinc.com)