

40 MIL COATED WOVEN PE

	ASTM TEST METHOD	40 MIL
UNIT WEIGHT	3776	17.1 OZ/SQ-YD
THICKNESS	D5199	40 MIL
GRAB STRENGTH	D775-00	WARP 690 LBF / WEFT 680 LBF
TONGUE TEAR	D775-00	WARP 56 LBF / WEFT 70 LBF
TRAPEZOIDAL TEAR	D775-00	WARP 65 LBF / WEFT 88 LBF
PUNCTURE RESISTANCE	D4833	TBD
HYDROSTATIC RESISTANCE	D775-00	TBD
MULLEN BURST	D3786	TBD
VOLATILE LOSS	D1203	0.04%
LOW TEMPERATURE FLEX	D2136	WARP/WEFT: PASS @ -30 DEG C (-22 DEG F)
DIMENSIONAL STABILITY	D1204	WARP -1.6% WEFT -1.6%
WVTR	E96	0.13 G/M ² 24 HRS
ACCELERATED UV WEATHERING	G154	>90% STRENGTH RETENTION AFTER 2000 HOURS



CONTACT US

SALES: Sam Liberto, 724.650.3592, sam@bepsinc.com

OPERATIONS: Jack Bell, 814.598.2553, jackb@bepsinc.com