

40 MIL COATED WOVEN XGL™ PE

	ASTM TEST METHOD	40 MIL
UNIT WEIGHT	D751	19.7 OZ/SQ-YD
THICKNESS	D1777	47 MIL
GRAB STRENGTH	D751	WARP 669 LBF / WEFT 654 LBF
TONGUE TEAR	D751	WARP 216 LBF / WEFT 213 LBF
HYDROSTATIC RESISTANCE	D751	542 PSI
MULLEN BURST	D3786	1224 PSI
PUNCTURE RESISTANCE	D4833	255 LB
ACCELERATED UV WEATHERING	G154	>90% STRENGTH RETENTION AFTER 2000 HOURS



CONTACT US

SALES: Sam Liberto, 724.650.3592, sam@bepsinc.com

OPERATIONS: Jack Bell, 814.598.2553, jackb@bepsinc.com