

**6-8 MIL STRING REINFORCED PP**

	ASTM TEST METHOD	R6BB	R6BW	R6WW	R8
APPEARANCE		BLACK/BLACK	BLACK/WHITE	WHITE/WHITE	BLACK/BLACK OR WHITE/WHITE
THICKNESS, NOMINAL		6 MIL	6 MIL	6 MIL	8 MIL
WEIGHT		3.5 OZ/SQ-YD	3.9 OZ/SQ-YD	4.0 OZ/SQ-YD	5.5 OZ/SQ-YD
CONSTRUCTION		EXTRUSION LAMINATED WITH SCRIM REINFORCEMENT			
TENSILE STRENGTH	D7003	60 LBF	60 LBF	60 LBF	60 LBF
ELONGATION AT BREAK	D7003	450%	450%	450%	600%
GRAB TENSILE	D7004	75 LBF	75 LBF	75 LBF	80 LBF
TRAPEZOIDAL TEAR	D4533	50 LBF	50 LBF	50 LBF	
TONGUE TEAR	D4533				30 LBF
MULLEN BURST	D751	60 PSI	60 PSI	60 PSI	70 PSI
CBR PUNCTURE RESISTANCE	D6241				240 LBF
MAX TEMP USE		180 DEG F	180 DEG F	180 DEG F	180 DEG F
MIN TEMP USE		-70 DEG F	-70 DEG F	-70 DEG F	-70 DEG F
WVTR	E96 A	0.03	0.03	0.03	0.03
PERM RATING (G/FT <sup>2</sup> .HR.IN.HG)	E96 A	0.07	0.07	0.07	0.066



**CONTACT US**

**SALES: Sam Liberto, 724.650.3592, sam@bepsinc.com**

**OPERATIONS: Jack Bell, 814.598.2553, jackb@bepsinc.com**