

8-12 OZ. FELT

	ASTM TEST METHOD	8 OZ	10 OZ	12 OZ
WEIGHT		8 OZ/SQ-YD	10 OZ/SQ-YD	12 OZ/SQ-YD
GRAB TENSILE	D4632	205 LBS	250 LBS	300 LBS
GRAB ELONGATION	D4632	50%	50%	50%
TRAPEZOIDAL TEAR	D4533	80 LBS	100 LBS	115 LBS
PUNCTURE RESISTANCE	D6241	525 LBS	625 LBS	825 LBS
UV RESISTANCE AFTER 500 HOURS	DR355	70% STRENGTH RETAINED	70% STRENGTH RETAINED	70% STRENGTH RETAINED
HYDRAULIC				
APPARENT OPENING SIZE	D4751	80 US STD SIEVE	100 US STD SIEVE	100 US STD SIEVE
PERMITIVITY	D4491	1.5 SEC ⁻¹	1.2 SEC ⁻¹	1.0 SEC ⁻¹
WATER FLOW RATE	D4491	110 GPM/SQ-FT	85 GPM/SQ-FT	75 GPM/SQ-FT



CONTACT US

SALES: Sam Liberto, 724.650.3592, sam@bepsinc.com

OPERATIONS: Jack Bell, 814.598.2553, jackb@bepsinc.com