

## 9-30 MIL COATED WOVEN

	ASTM TEST METHOD	9 MIL	12 MIL	16 MIL	20 MIL	24 MIL	30 MIL
<b>WEIGHT</b>		5.4 OZ/SQ-YD	6.0 OZ/SQ-YD	7.6 OZ/SQ-YD	9.7 OZ/SQ-YD	12.0 OZ/SQ-YD	18.0 OZ/SQ-YD
<b>THICKNESS</b>		9 MIL	12 MIL	16 MIL	20 MIL	24 MIL	30 MIL
<b>GRAB TENSILE</b>	D751-95	WARP 210 LB / WEFT 145 LB	WARP 198 LB / WEFT 194 LB	WARP 340 LB / WEFT 180 LB	WARP 363 LB / WEFT 334 LB	WARP 506 LB / WEFT 385 LB	WARP 400 LB / WEFT 420 LB
<b>TONGUE TEAR</b>	D4533	WARP 55 LB / WEFT 55 LB	WARP 75 LB / WEFT 62 LB	WARP 132 LB / WEFT 55 LB	WARP 132 LB / WEFT 112 LB	WARP 132 LB / WEFT 110 LB	WARP 130 LB / WEFT 140 LB
<b>MULLEN BURST</b>	D6241	325 PSI	360 PSI	400 PSI	650 PSI	750 PSI	780 PSI
<b>ACCELERATED UV WEATHERING</b>	D4533	80% STRENGTH RETENTION AFTER 2000 HOURS	90% STRENGTH RETENTION AFTER 2000 HOURS	90% STRENGTH RETENTION AFTER 2000 HOURS	90% STRENGTH RETENTION AFTER 2000 HOURS	90% STRENGTH RETENTION AFTER 2000 HOURS	90% STRENGTH RETENTION AFTER 2000 HOURS



**CONTACT US**

**SALES:** Sam Liberto, 724.650.3592, [sam@bepsinc.com](mailto:sam@bepsinc.com)

**OPERATIONS:** Jack Bell, 814.598.2553, [jackb@bepsinc.com](mailto:jackb@bepsinc.com)